

## Title of the Invention

### Thin-walled Honeycomb Structure and Method for Reinforcing the Same

5

## Background of the Invention and Related Art Statement

The present invention relates to a honeycomb structure to be suitably used as a catalyst carrier for purifying automobile exhaust gas. More particularly, the present invention relates to a thin-walled honeycomb structure that has thin partition walls, a light weight, a small loss of pressure, and an improved mechanical strength by virtue of reinforcing a circumferential portion of the honeycomb structure not so as to give the damages to the honeycomb structure during its manufacturing or its handling, and a method for reinforcing such a thin-walled honeycomb structure.

There has conventionally used, as a carrier for catalysts of automobile exhaust gas(hereinafter referred to as a catalyst for purifying exhaust gas), a ceramic honeycomb structure having (a) numerous cell passages defined by a plurality of partition walls and (b) a circumferential wall surrounding the cell passages(hereinafter referred to as a honeycomb structure). That is, the conventionally used exhaust gas catalysts have been produced by coating a honeycomb structure with a  $\gamma$ -alumina to form a layer thereof, and loading a catalytic component such as a noble metal or the like into

inner surfaces of pores of thus formed  $\gamma$ -alumina layer.

More concretely, a honeycomb structure has usually been produced by the steps of extrusion-molding a material, which mainly becomes cordierite when it is fired, through a nozzle having lattice-  
5 like slits so as to form integratedly a honeycomb portion and a circumferential wall, and subsequently drying and firing thus molded article. Thus obtained honeycomb structure is transferred to a step of forming the catalytic layer by firstly coating the inner surfaces of numerous cell passages with  $\gamma$ -alumina so as to form a  $\gamma$ -  
10 alumina layer thereon, and then loading a noble metal component, as a catalytic component, such as platinum, rhodium, or palladium into inner surfaces of pores of thus formed  $\gamma$ -alumina layer. Then, the honeycomb structure is subjected to baking treatment at a temperature of about 600°C so as to back the catalytic component  
15 thereon to give a catalyst for purifying exhaust gas. Thus produced catalyst for purifying exhaust gas is housed in a metallic container with aid of a cushioning material. The metallic container, i.e., a converter is connected to an exhaust pipe by means of welding, bolting, or the like, to set up an engine for an automobile, etc.

20 Recently, regulations on exhaust gases have become strict year by year, especially in developed countries, in consideration of environmental problems. To cope with these stricter regulations, an ever-lasting improvement in purification ability is required for a catalyst for purifying exhaust gas. On the other hand, a desire to  
25 lower fuel charge and increase output of power has been evident in

the fields of engine development. Because of such a situation, the reduction in pressure loss during operation has been required in the case of the catalyst for purifying exhaust gas. In the case of the catalyst for purifying exhaust gas, so as to solve problems mentioned  
5 above, there have become evident such a strong movement that the improvement in the performance of the catalyst for purifying exhaust gas at the time of warming up of the engine has been tried by increasing a passage area of the cell passages so as to reduce pressure loss, and lightening the weight of the catalyst for purifying  
10 exhaust gas itself so as to reduce its heat capacity by making the partition walls thin without decreasing the number of cells as well. Hitherto, a honeycomb structure having partition walls of 0.15 mm or more in the thickness was most popular. However, a honeycomb structure having partition walls having of 0.13 or less, particularly,  
15 0.11 mm or less in the thickness has recently come to be popular.

However, to make partition walls of a honeycomb structure thinner causes a problem that the extremities(hereinafter sometimes referred to as a corner) of circumferential portions of the honeycomb structure are often broken during manufacturing, handling, or  
20 conveying the honeycomb structure, or housing the honeycomb structure into the container for converter so as to set it in an engine because the structural strength of the honeycomb structure is consequently decreased, particularly in the circumferential portions of the honey-comb structure. This phenomenon becomes evident  
25 when the partition walls of the honeycomb structure becomes thinner.

This is because damages have recently come to be caused in a honeycomb structure more frequently in accordance with thinning of partition walls in a honeycomb structure. Note that the honeycomb structure is liable to break when an external force such as a mechanical shock is applied thereto during transportation or the like, even in the case of the honeycomb structure having thicker partition walls. This is because a ceramic material is inherently brittle. Thus, the breaking of the honeycomb structure was also occasionally reported. Because of its very low frequency, however, it has not particularly been regarded as a problem.

Further, the frequency of the deformation in partition walls during extrusion-molding has remarkably increased as partition walls become thinner; while in the case of the conventional honeycomb structures having such thicker partition walls as the thickness of 0.15 mm or more, such a problem is no so serious. This is because the circumferential wall has a thickness of at least 0.3mm, and therefore, the strength in the circumferential portions can be ensured to a certain degree. The deformation in partition walls tends to be caused particularly at the vicinity of the circumferential walls in the circumferential portions. Its major cause is considered to be the failure to attain uniform extrusion-molding because of the unbalance in the fluidity of a raw material between the honeycomb portions and the vicinity of the circumferential partition walls, in the case where the circumferential walls are made thicker than partition walls in a honeycomb structure so as to ensure strength in a

circumferential portion.

A similar phenomenon to the case where cordierite is used in the deformation of the partition walls in the honeycomb structure is also observed when a ceramic material such as alumina, mullite, silicon nitride, silicon carbide, or zirconia is subjected to an extrusion-molding. This is because, as a starting material, a material prepared by mixing and kneading said material with water and a binder is used as well. Since the deformation in partition walls is mainly attributed to buckling derived from compressive load, a similar problem is also observed in not only a honeycomb structure having square cells, but also a honeycomb structure having rectangular, triangular, or hexagonal shape.

Some proposals have been made to solve the various problems derived by making partition walls thinner in a honeycomb structure. Firstly, it has been proposed to make the thickness of the circumferential walls from 0.3mm to 0.1mm so as to near the thickness of the circumferential walls to a thickness of the partition walls, in order to improve the balance in the flow amount of a raw material during molding. In this case, however, the strength in the circumferential wall is not sufficient. In other words, when circumferential walls are too thin, a breaking starts at the circumferential walls due to its insufficient rigidity. The thickness of at least 0.1mm, desirably at least 0.15 mm is sufficient just to house the honeycomb structure into a container kept under a uniform and static external pressure as a thickness for circumferential walls. However, such a

thickness for the circumferential walls is not sufficient to resist against external pressure such as a mechanical shock given during transporting the honeycomb structure or the like.

On the other hand, there has been made such a proposal that  
5 the strength against mounting pressure of the circumferential walls would increase if the thickness of the circumferential walls is made thicker. Thus, a cordierite honeycomb structure having square cells, a partition wall thickness of 0.11mm, and such a thickness of at least 0.4mm as circumferential walls was prepared so as to increase  
10 strength. On contrary to expectation, however, it was found, as a result of an isostatic strength test, that the honeycomb structure was not improved in strength and had a tendency of deterioration in strength. The investigation was made so as to clarify the reason why the isostatic strength could not improve when only the thickness of  
15 the circumferential walls was made thicker. As a result, it has been found that partition walls (ribs) around cells in the circumference in a molded article are deformed to a great extent just after extrusion-molding, and that the number of deformed partition walls increases as the circumferential wall is made thicker.

20 This is because, if the circumferential wall is made thicker, an amount of a raw material passing through slits for forming the circumferential walls increases when the raw material passes through slits of the nozzle upon extrusion-molding. As a consequence, partition walls of circumferential cells are dragged toward the  
25 circumferential walls, or the circumferential walls press the internal

partition walls of the honeycomb structure. Thus, it has been evident that the remarkable gap in the unbalance between a flow of the raw material for the circumference wall and a flow of the raw material for the partition walls is considered to be a major cause. Further, the thinning of the partition walls brings buckling deformation more easily. In addition, the circumferential wall and partition walls in the circumferential portion are deformed by the weight of the honeycomb structure itself at the time when a honeycomb structure is supported by a jig on the surface of the circumferential walls right after extrusion-molding. These are also considered to be the major causes.

If the internal partition walls of the honeycomb structure is molded straight, the breakage of the honeycomb structure starts owing to the compression of the partition walls when pressure is given to the honeycomb structure from the surface side of the circumferential wall. This is because the internal portion of the honeycomb structure is theoretically the center of compressive stress. However, in the case that partition walls at the vicinity of the circumferential portion is deformed, or that the circumferential wall is extremely thin, bending stress, i.e., a tensile stress is generated at the position of partition walls of the honeycomb structure. Since a ratio of tensile strength to compressive strength is generally as low as about 1:10, the honeycomb structure starts to break if it has deformed partition walls when even only very lower strength is given thereto.

On the other hand, even if the circumferential wall can be

made considerably thick at the time of molding, a great difference in heat capacity exists between the honeycomb portion having thin partition walls and the thick circumferential wall, thereby the thermal shock resistance of the honeycomb heater is lowered.

5           In order to solve the problems derived from an extreme difference in thickness between the honeycomb portion and the circumferential portion, there has been made the following proposal; a molding is carried out, with the adjustment of a raw material flow at the time of extrusion, by making partition walls in the circum-  
10   ferential portion and the circumferential wall thicker so as to enhance pressure resistance in an axial direction of the honeycomb structure and a molding is carried out by adjusting. However, since the adjustment of balance is very subtle when this means is used, it becomes more difficult to suppress deformation in the partition walls  
15   as the circumferential wall becomes thicker. Furthermore, the thicker circumferential portion gives a greater influence on its own heat capacity. In this case, the difference in temperature between inside and outside the circumferential wall is increased; thereby thermal shock resistance of the honeycomb structure is inevitably decreased.  
20   Furthermore, since such means brings about an increase in weight of the honeycomb structure, the performance of the catalyst after of an engine is warmed up is lowered. Furthermore, it is not so preferable due to the pressure loss problem.

          Thus, numerous studies have conventionally been made so as  
25   to solve the various problems caused in accordance with thinning of



partition walls in a honeycomb structure. However, the problems have not been solved yet. Under such conditions, the present inventor paid attention to reinforcement of the circumferential portion, particularly its edge portion, in the honeycomb structure.

5           There has been known a method of reinforcing a honeycomb structure. In the method, a coat layer is formed by applying a ceramic material as a reinforcing material for reinforcement of the circumferential portion on the circumferential wall without unitarily forming the thick circumferential wall by extrusion molding, or  
10   filling the reinforcing material into cells in the circumferential portion. However, this method has drawbacks such as, for example, the reduction in the thermal shock resistance of the honeycomb structure during the practical use, the occurrence of the detachment in the coat layer due to cracks generated in the coat layer, the  
15   formation of the cracks that sometimes reaches to the honeycomb structure due to the shrinkage of the coat layer itself caused by a high temperature generated during engine operation, and the like.

          There has been known another method, in which a resin is coated on the surface of the circumferential portion. The aim of this  
20   method is to prevent loading of catalyst on the surface of the circumferential wall, and therefore, a water-repellent resin film is formed on the surface of the circumferential wall by using a resin material having low strength such as vinyl acetate, fluororesins, or silicone resins. Thus, in the method it is not intended to reinforce the  
25   circumferential portion of the honeycomb structure. Therefore, the

film formed is thin since this film is formed not so as to reinforce the circumferential portion. In fact, the thin film does play any active role in the reinforcement of the circumferential portion.

## 5 Summary of the Invention

The present invention has been made, taking into consideration the aforementioned conventional problems. Thus, the aim of the present invention is to provide a honeycomb structure having not  
10 only sufficient catalytic properties, mechanical strength, and thermal shock resistance, but also having reinforced circumferential portion not so as to be damaged during manufacturing or handling the honeycomb structure. According to the present invention, there is provided a thin-walled honeycomb structure comprising:

15                   a circumferential wall,  
                  numerous partition walls disposed inside the circumferential wall, and  
                  numerous cell passages defined by the partition walls;  
                  wherein a circumferential portion of the honeycomb structure  
20 is reinforced wholly or in a part within a certain distance from an extremity surface of the honeycomb structure by a reinforcing material which dissipates, or evaporates at a high temperature.

In a thin-walled honeycomb structure of the present invention, an organic high molecular material having high strength or high  
25 elasticity is preferably used as a reinforcing material. Each of the

partition walls of the honeycomb structure has a thickness of 0.13 mm or less. A cross section of a cell passage preferably has a triangular, square, rectangular, hexagonal, or circular shape. As a material for the honeycomb structure, there can be preferably used at least one kind of porous ceramic material selected from a group consisting of cordierite, alumina, mullite, silicon nitride, silicon carbide, and zirconia.

According to the present invention, there is further provided a method for reinforcing a thin-walled honeycomb structure comprising:

a circumferential wall,  
numerous partition walls disposed inside the circumferential wall, and  
numerous cell passages defined by the partition walls;  
wherein a circumferential portion of the honeycomb structure is coated wholly or in a part within a certain distance from an extremity surface of the honeycomb structure with an organic high molecular material.

Preferably, this method for reinforcing a thin-walled honeycomb structure, comprises the steps of:

impregnating and/or coating a circumferential portion of the honeycomb structure with an organic high molecular material wholly or in a part within a certain distance from an extremity of the surface of the honeycomb structure, and  
curing the organic high molecular material.

Also this method can preferably comprise the steps of:

pouring an organic high molecular material into cell passages at least located at the vicinity of a circumferential portion inclusive of a foremost outer circumferential portion of the honeycomb structure so as to coat or fulfil inner surfaces of said cell passages with said material, and curing the material.

It is also preferable that a circumferential portion of the honeycomb structure is wrapped up wholly or in a part within a certain distance from an extremity surface of the honeycomb structure with a tape formed by molding an organic high molecular material. The tape is preferably a pressure-sensitive adhesive, and the organic high molecular material is a photo-curable photo-reactive material. At least the circumferential portion of the end surface of the honeycomb structure is preferably reinforced with an organic high molecular material after injection molding, or after drying before firing but after injection molding, thereby the productivity is improved.

## **20 Brief Description of the Drawings**

Fig. 1 is a perspective view showing an embodiment of a thin-walled honeycomb structure of the present invention.

## Mode for Carrying Out the Invention

A thin-walled honeycomb structure of the present invention has the same structure and basic shape as a conventionally known general honeycomb structure. As shown in a perspective view of Fig. 1, the thin-walled honeycomb structure is constituted by a circumferential wall 2, numerous partition walls 3 disposed inside the circumferential wall 2, and numerous cell passages 4 (cells 4) defined by the partition walls 3. Though each of the cells 4 has a square shape (sectional shape) in Fig. 1, it may also be triangular, rectangular, hexagonal, circular, or the like.

As a material forming a thin-walled honeycomb structure 1, there is preferably used at least one porous ceramic material selected from the group consisting of cordierite, alumina, mullite, silicon nitride, silicon carbide, and zirconia. Extrusion molding is preferably employed for the molding. A honeycomb heater having almost uniform thickness wholly including the circumferential portion has an advantage of being molded easily and improvement in a compressive rupture strength. The circumferential wall 2 is preferably thin in view of thermal shock resistance. However, the circumferential wall 2 of the thin-walled honeycomb structure 1 is required to have a structural strength sufficient to resist to mounting pressure to be kept in a converter container. For this reason, it is known from experience as an artisan in the technical field of this invention or analysis of FEM value that the circumferential wall 2

preferably has a thickness of at least 0.1mm, preferably 0.2mm or more.

An improvement in strength pressure resistance of the thin-walled honeycomb structure 1 in the converter container is derived from the formation of the catalytic layer in the thin-walled honeycomb structure 1. That is, during the time when the catalytic layer is formed,  $\gamma$ -alumina is coated on surfaces of partition walls 3 in the thin-walled honeycomb structure 1, thereby structural strength of the thin-walled honeycomb 1 is improved. Therefore, as far as the reinforcement of the circumferential portion of the thin-walled honeycomb structure 1 is retained during the period from the step of molding to the step of housing the honeycomb structure 1 in the converter container, the thin-walled honeycomb structure 1 may not be damaged. Needless to say, the thin-walled honeycomb structure 1 is required not to show any inconvenience such as damaging under operational conditions after the honeycomb structure 1 is housed in the converter container. From such a viewpoint, the thickness of the partition walls 3 is 0.13mm or less in the case of the thin-walled honeycomb structure 1 according to the present invention.

From the above viewpoint, in the case of the thin-walled honeycomb structure according to the present invention, the circumferential portion (external surface of the circumferential wall 2) of the honeycomb structure is reinforced wholly or in a part within a certain distance from an extremity of the surface of the honeycomb structure (i.e., an edge portion) by a reinforcing material such as an

organic high molecular material(hereinafter sometimes referred to as "resin") may dissipate, or evaporate at a high temperature. That is, unlike any conventional method, the circumferential portion is reinforced not with a material such as ceramic having thermal resistance, but with a resin having high strength and high elasticity, particularly a resin which dissipates or evaporates at a high temperature, for example, which may dissipate or evaporate at a relatively low temperature of 300°C or less. The term dissipates or evaporates means hereinafter an action required for removing a resin used for reinforced according to the present invention by running off a melted resin after melting it at a high temperature, decomposing a resin at a high temperature, by gasifying it at a high temperature, or the like. That is, any action may be included in the above-mentioned term, as far as a resin used for reinforced according to the present invention can be removed thereby, without giving any adverse effect on the molded article according to the present invention.

The circumferential portion is reinforced with an elastic layer from the molding step of the thin-walled honeycomb structure to the formation step of catalytic layer. On the other hand, since a coat layer of such a resin in the circumferential portion evaporates during a treatment at a high temperature over 500°C, the coat layer is not present during using a catalytic converter and does not give any adverse affect on the performance of the converter.

Since a resin is an adhesive, an elastomer, a rubber, or the like, a liquid resin is cured to exhibit an adequate strength and to absorb

an impact because of its elasticity. Further, a resin is cheap and is easily obtainable because it has widely used. Furthermore, the application of a resin on the honeycomb structure may be easy, and in various manners. Therefore, a resin is suitable in the aspects of mass  
5 productivity and cost.

The following method can be given, as an exemplary method for reinforcing the circumferential portion of the thin-walled honeycomb structure: a method which comprises impregnating the thin-walled honeycomb structure with a resin in an entire surface of  
10 the circumferential wall or in an extremity portion, and/or coating a resin the surface of the circumferential wall with a resin, and then curing thus coated resin. That is, the resin permeates from the surface into the inside of the circumferential walls to reinforce the circumferential wall itself and the surface of the circumferential wall.  
15 Examples of resins include various kinds of adhesives such as thermosetting resins such as epoxy resins, elastic resins such as silicone resins, and ultraviolet curing resins such as acrylic resins; elastomers such as silicone; rubber materials; and pressure-sensitive adhesives.

20 Since a thermosetting adhesive has a high adhesive strength and a high shear strength, impregnating the circumferential portion with a thermosetting adhesive with the utilization of capillary phenomenon, and then curing the thermosetting adhesive can improve the strength of the circumferential portion. When a  
25 thermosetting resin is used, as an adhesive layer, so as to protect the



surface of the circumferential portion of the honeycomb structure by coating the surface with the resin, an additive may be added to the thermosetting resin to improve its shock resistance. Such an additive may include a thermoplastic resin such as nylon; a rubber material  
5 such as a nitrile rubber and a silicone rubber, an elastic elastomer; or a fiber material such as glass fibers, cellulose, or the like. This is because thermoplastic resins generally have a low shock resistance.

It is possible to use an elastic elastomer adhesive alone. A liquid prepared by mixing a curing agent with a resin can be coated  
10 on the entire surface of the circumferential wall of the thin-walled honeycomb structure in various methods such as spraying, brushing, and printing. In the case of trying to improve productivity by shortening a time of curing of the resin, an ultraviolet curing type resin such as an acrylate or an epoxy resin may be used. In this case,  
15 it is preferable to improve shock resistance by mixing an elastic elastomer or the like with the ultraviolet curing resin. By coating the surface of the circumferential portion, the effect of not to load a catalyst on the surface of the circumferential portion can be expectable as in conventional techniques.

20 As an additional preferable method for reinforcing the circumferential portion of the thin-walled honeycomb structure, there is given a method comprising the step of coating surfaces of the cell passages by putting a resin in the cell passages in the periphery of the circumferential portion including at least cells in the  
25 outermost circumferential portion of the thin-walled honeycomb

structure, or by filling a resin into the cell passages, and curing the resin. In this case, a resin used in the aforementioned method of reinforcement can be used.

As a method which does not need a curing treatment such as heating, irradiation of light, or the like, the entire surface or the edge portion of the circumferential portion of the honeycomb structure is wrapped up with a tape formed by molding an organic high molecular material. In this case, a pressure-sensitive adhesive in which a plasticizer, or a filler is mixed with a rubber material using an adhesive property can be used. A tape-like adhesive can be easily coated on the surface of the circumferential wall of the thin-walled honeycomb structure by winding the tape round the surface. Further, the tape may be easily peeled.

As described above, the circumferential portion of the fired thin-walled honeycomb structure is reinforced usually. When a molded body or dried body of the thin-walled honeycomb structure is conveyed to a distant place before being fired, the circumferential portion of the thin-walled honeycomb structure is liable to be damaged during transportation. Therefore, it is preferable that at least the edge portion of the thin-walled honeycomb structure is reinforced with the aforementioned various resins after extrusion molding or drying after extrusion molding and before firing. Of course, the entire surface of the circumferential wall may be reinforced. Thus, production efficiency can be improved.

The present invention is hereinafter described in more detail

by means of examples. However, the present invention is by no means limited to the examples.

### Example

5           Generally, a honeycomb structure (carrier) for purifying exhaust gas is required for isostatic strength and thermal shock resistance as an index durable under for practical conditions for use as a structural body besides the performances as to loading ability of a catalyst and lowness in pressure loss. Isostatic strength is  
10       prescribed as an index of external pressure resistance in automobile standards (JASO standards) M505-87 issued by Shadan Hojin Jidousha Gijutukai (Association of Automobile Technology). However, any index of external pressure resistance during handling or transportation is not particularly prescribed in it.

15           Therefore, in Examples there was used, as an index of external pressure resistance during handling or transportation the honeycomb structure, well-known Charpy impact test to evaluate the honeycomb structures for strength against impact due to a collision with something during transportation or falling. In the Charpy  
20       impact test, a hammer is swung up and then swung down to hit the surface of the circumferential wall of the honeycomb structure. The difference between the angle of the first swinging up and the angle of rebounding shows impact rupture energy. In this test, evaluation was done by using the impact rupture energy, when the surface is  
25       ruptured, as a strength of a honeycomb structure.

T a b l e 1

	Method for reinforcing circumferential portion	Cell density (gps)	Thickness of partition wall (mm)	Thickness of circumferential wall (mm)	Impact rupture energy (kg-cm)
Comp. Ex. 1	A ceramic was filled into 10 mm cell passages in circumferential portion, and the honeycomb structure was fired again.	300	0.3	0.3	3.3
Comp. Ex. 2	The circumferential portion and 10 mm cell passages were impregnated with a ceramic, and the honeycomb structure was fired again.				3.8
Comp. Ex. 3	No reinforcement				1.5
Comp. Ex. 4	No reinforcement	400	0.13	0.3	0.9
Comp. Ex. 5	No reinforcement	400	0.09	0.25	0.6
Comp. Ex. 6	No reinforcement	900	0.05	0.2	0.5
Comp. Ex. 7	The circumferential portion and 10 mm cell passages were impregnated with a ceramic, and the honeycomb structure was fired again.	400	0.11	0.15	2.0
Comp. Ex. 8	The circumferential portion and 10 mm cell passages were impregnated with a ceramic, and the honeycomb structure was fired again.			0.3	2.5
Example 1	The circumferential portion and 10 mm cell passages were impregnated with a resin to be cured.			0.15	2.2
Example 2	The circumferential portion and 10 mm cell passages were impregnated with a resin to be cured.			0.3	2.6
Example 3	An elastic resin was applied on the circumferential portion and cured.			0.15	2.7
Example 4	An elastic resin was applied on the circumferential portion and cured.			0.3	3.3
Example 5	A resin was filled into cells in the circumferential portion, and the resin was cured.			0.15	2.8
Example 6	A resin was filled into cells in the circumferential portion, and the resin was cured.			0.3	3.2
Example 7	An adhesive tape was stuck on the circumferential portion.			0.15	2.9
Example 8	An adhesive tape was stuck on the circumferential portion.			0.3	3.5
Example 9	An adhesive tape was stuck on the circumferential portion.	400	0.09	0.15	2.1
Example 10	An adhesive tape was stuck on the circumferential portion.			0.25	2.8
Example 11	An adhesive tape was stuck on the circumferential portion.	600	0.06	0.15	2.2
Example 12	An adhesive tape was stuck on the circumferential portion.			0.25	2.7
Example 13	An adhesive tape was stuck on the circumferential portion.	900	0.05	0.15	1.9
Example 14	An adhesive tape was stuck on the circumferential portion.			0.2	2.5

Table 1 shows methods for reinforcing the circumferential portions of the honeycomb structures having various structures and factors (cell density, thickness of partition walls, thickness of circumferential walls) of the shapes. The honeycomb structures were produced as examples of the present invention and comparative examples of prior art. The cordierite type honeycomb structures having a diameter of 106 mm and a length of 155mm and having been obtained by firing an extruded and dried articles produced from kneaded material of talc, kaolin, alumina, or the like are used as respective testing samples for Examples and Comparative Examples.

In each of the Examples 1 and 2, the surface of the circumferential wall was impregnated with a resin. A mixture liquid having an adequately low viscosity was prepared by mixing a polyamide curing agent, a solvent, and a plasticizer with a commercially available epoxy resin. A honeycomb structure in which the entire surface of the end was masked with a tape was immersed in the liquid by about 10 mm from its extremity so that the circumferential wall of the honeycomb structure was impregnated with the liquid. After the surface of the circumferential wall was coated with the resin liquid to a certain degree, the honeycomb structure was taken out, and the resin liquid sticking to the circumferential wall was wiped off. The honeycomb structure was put in a drying container so as to be subjected to a thermal curing treatment at about 150°C for 30 minutes.

In Examples 3 and 4, a resin was applied on the

circumferential wall. An adhesive which had been prepared by mixing a nitrile rubber with a commercially available thermosetting phenol resin was applied on the circumferential wall, thereby an adhesive layer having a thickness of 1 – 2 mm and a width of about 10  
5 mm from the extremity of the honeycomb structure was formed over the whole circumference of the circumferential wall. Then the honeycomb structure was subjected to heat-curing treatment at about 180°C for 30 minutes.

In Examples 5 and 6, a resin was filled into cells in the  
10 circumferential portion. First, a mixture liquid having an adequately low viscosity was prepared by adding a polyamide curing agent, a solvent, and a plasticizer to an epoxy resin. A honeycomb heater whose extremity was masked with a tape so as to exclude cells in the most circumferential portion was immersed in the liquid by about 10  
15 mm. After the liquid was filled into the cells, the honeycomb structure was taken out. The liquid sticking to the surface of the circumferential wall was wiped off. Then, the honeycomb structure was put in a drying container and subjected to a heat-curing treatment for about 150°C for 30 minutes.

20 In Examples 7 – 14, a tape was put on the surface of the circumferential wall. A rubber pressure-sensitive adhesive was applied on one side of a thin sheet. An adhesive tape having a thickness of 1 – 2mm was cut so as to have a width of about 10mm. The tape was wound around the circumferential wall with being  
25 pressed against the surface of the wall to cover the range within

about 10mm from the end of the honeycomb structure.

On the contrary, honeycomb structures each having a thick partition wall was used in Comparative Examples 1 - 3. In Comparative Example 1, a ceramic material was filled into the cell passages in the circumferential portion, and the honeycomb structure was subjected to firing again. In Comparative Example 2, the cell walls in the circumferential portion were impregnated with a ceramic material, and the resulting honeycomb structure was subjected to firing again. In Comparative Example 3, any reinforcement was not employed. In Comparative Examples 4 - 6, honeycomb structures each having thin walls without any reinforcement in the circumferential portion was used. In Comparative Examples 7 and 8, honeycomb structures each having thin walls was used. The cell walls in the circumferential portion were impregnated with a ceramic material, and the resulting honeycomb structure was subjected to firing again.

The results of the test are shown in Table 1. From comparison among the results, it is found that a structural strength (impact strength in the circumferential portion) of the honeycomb structures of the Examples is about the same as that of the honeycomb structures having thick partition walls of the prior art as in Comparative Examples 1 and 2. It is further found that the honeycomb structures whose circumferential portion is reinforced according to the present invention needs particularly high rupture energy, i.e., it shows a high resistance against the rupture, in

comparison with Comparative Examples 4 - 7 whose circumferential portions were not reinforced. The same thing is also observed when the results of the Examples are compared with Comparative Examples 8 and 9 whose circumferential portions were reinforced  
5 with a ceramic material.

As described above, according to the thin-walled honeycomb structure and the method for reinforcing the thin-walled honeycomb structure of the present invention, it becomes possible to remarkably reduce frequency of damages during handling or transportation of  
10 the honeycomb structure. This is because the honeycomb structure can be easily molded because of the small difference in thickness between the honeycomb portion and the circumferential wall, and by virtue of the reinforcement in the circumferential portion. When such a honeycomb structure is used as a carrier for an automobile exhaust  
15 gas purification catalyst, a loss in pressure is small, and heat capacity of the catalyst is reduced since the partition walls are thin. As a consequence, the present invention can improve purification ability during the period the engine has been warmed up.